

<b>Product Full Name:</b>	5000 DTEX FIBRILE YARN
<b>Style:</b>	FIBRILLATED YARN
<b>Basic Polymer:</b>	PE
<b>Color:</b>	ANY COLOR
<b>Aspect:</b>	FIBRILLATED

SPECIFICATIONS	UNIT	AVERAGE VALUE*
Yarn Count <sup>1</sup>	TEX	500 ±5%
	denier	4500 ±5%
Yarn Width	mm	5,5 ±2%
Yarn Thickness	μ	100 ±5%
Twist <sup>4</sup>	Turns/m	28 ±10%
Twist Direction		Z

TEST SCORES	UNIT	AVERAGE VALUE*
Strength at Break <sup>2</sup>	N	> 50
Elongation at Break <sup>2</sup>	%	< 75
Shrinkage at 130°C <sup>3</sup>	%	< 3
Lubrication	%	APP. 1,5

RESISTANCE VALUE	UNIT	AVERAGE VALUE*
UV Stabilizer <sup>5</sup>	%	3%

\* Average value are based on the mean values of 10 different bobbins

1) TS 244 EN ISO 2060 2) TS EN ISO 2062 3) ASTM D 22559 4) TS 247 EN ISO 2061 5)BS EN 14836 2005 6,7) in house method

**Additional Information**

For more detailed information about our products, please contact us below.

<b>Address:</b> Başpınar (Organize) OSB Mah. 2.Bölge 83206 Nolu Cadde, D.No :3 27620 Şehitkamil/Gaziantep/ TÜRKİYE	<b>Phone :</b> +90 342 337 32 26 <b>E-Mail:</b> info@bulutsentetik.com
--	---