

<b>Product Full Name:</b>		8000 DTEX FIBRILE YARN	
<b>Style:</b>		FIBRILLATED YARN	
<b>Basic Polymer:</b>		PE	
<b>Color:</b>		ANY COLOR	
<b>Aspect:</b>		FIBRILLATED	
<b>SPECIFICATIONS</b>	<b>UNIT</b>	<b>AVERAGE VALUE*</b>	
Yarn Count <sup>1</sup>	TEX	800 ±5%	
	denier	7200 ±5%	
Yarn Width	mm	10 ±2%	
Yarn Thickness	μ	100 ±5%	
Twist <sup>4</sup>	Turns/m	28 ±10%	
Twist Direction		Z	
<b>TEST SCORES</b>	<b>UNIT</b>	<b>AVERAGE VALUE*</b>	
Strength at Break <sup>2</sup>	N	> 70	
Elongation at Break <sup>2</sup>	%	< 70	
Shrinkage at 130°C <sup>3</sup>	%	< 3	
Lubrication	%	APP. 1,5	
<b>RESISTANCE VALUE</b>	<b>UNIT</b>	<b>AVERAGE VALUE*</b>	
UV Stabilizer <sup>5</sup>	%	%2-3%	
<b>* Average value are based on the mean values of 10 different bobbins</b>			
1) TS 244 EN ISO 2060 2) TS EN ISO 2062 3) ASTM D 22559 4) TS 247 EN ISO 2061 5)BS EN 14836 2005 6,7) in house method			
<b>Additional Information</b>			
For more detailed information about our products, please contact us below.			
<b>Address:</b> Başpınar (Organize) OSB Mah. 2.Bölge 83206 Nolu Cadde, D.No :3 27620 Şehitkamil/Gaziantep/ TÜRKİYE		<b>Phone :</b> +90 342 337 32 26 <b>E-Mail:</b> info@bulutsentetik.com	
Doküman No:KK.FR.15 Yayın Tarihi:21/09/2021 Rev.No/Tarih:00/...			